

Technical data sheet Stansa 161 foil

Type : O161400TYPGR2

Mass per unit area Gewicht per oppervlakte- eenheid Masse je Flächeneinheit	DIN 53854	g/m ²	161	
Thickness Dikte Dicke	DIN 53855	Mm	0.47	
			Machine direction Machine richting Längs	Cross direction Dwars richting Quer
Max. tensile strength Max. treksterkte Höchstzugkraft	DIN EN ISO 10319	kN/m	10.7	10.7
Elongation at max. tensile strength Rek bij max. treksterkte Höchstzugkraftdehung	DIN EN ISO 10319	%	53,0	56,1
Water permeability Water doorlaatbaarheid Wasserdurchlässigkeit	None			
Static Puncture	DIN EN ISO 12236	N	1625	
Cone penetration	DIN EN 918	Mm	30	

December 2004

The data are average values and indicative.

De gegevens zijn gemiddelde waarden en indicatief.

Die angegebene Werte sind durchschnittlichen Mittelwerte und Indikativ.

Because we all need room to grow!

